

Spin dynamics of the doped t-J model

R. Eder and Y. Ohta

Department of Applied Physics, Nagoya University, Nagoya 464-01, Japan

Using the exact diagonalization technique we study the low energy spin excitations in moderately doped (hole concentration < 25%) finite clusters of $t-J$ model. To clarify whether a given low energy spin excitation corresponds to a particle-hole transition in the ‘quasiparticle band’ near the Fermi energy, we compare the electron addition and removal spectra of the respective final state to that of the ground state. We find that the low energy spin excitation spectrum is composed of different branches, with the dominant low-energy spin excitation at (π, π) being a spin-wave like collective mode, whereas the low energy spin excitations with momentum transfer other than (π, π) correspond to particle-hole excitations.

pacs 74.20.-Z, 75.10.Jm, 75.50.Ee

The spin dynamics of strongly correlated electron systems is a key issue for the understanding of high-temperature superconductors. As an experimental fact, neutron scattering experiments show a broad peak in the dynamical spin correlation function for in-plane momentum transfer (π, π) at low frequencies $\sim 40\text{meV}$ [1]. Exact diagonalization studies of small clusters of $t-J$ model usually reproduce this behaviour [2,3], and it is the purpose of the present work to distinguish between different interpretations which are possible for this peak: within a weak coupling-like picture, the dynamical spin susceptibility is determined by particle-hole excitations of either real electrons or ‘spinons’, the strong scattering intensity for momentum transfer (π, π) then would be the consequence of Fermi surface nesting. A different interpretation would be to attribute the peak to the remnants of the short wavelength spin waves present in the undoped compounds; as long as their wavelength is shorter than the spin correlation length, such spin wave like excitations might well persist, but being no longer the Goldstone modes associated with antiferromagnetically broken symmetry, a finite frequency would be naturally expected [4]. Our results show that in finite $t-J$ model clusters (lattice size ≤ 20) with low hole concentration the second interpretation is the correct one: the dominant low-energy peak at (π, π) corresponds to a collective spin wave-like mode, particle hole excitations are restricted to different momentum transfer. The $t-J$ model reads:

$$H = -t \sum_{\langle i,j \rangle, \sigma} (\hat{c}_{i,\sigma}^\dagger \hat{c}_{j,\sigma} + H.c.) + J \sum_{\langle i,j \rangle} (\mathbf{S}_i \cdot \mathbf{S}_j - \frac{n_i n_j}{4}).$$

Here the $\mathbf{S}_i$ are the electronic spin operators and the sum over $\langle i, j \rangle$ stands for a summation over all pairs of nearest neighbors. The operators $\hat{c}_{i,\sigma}$ are expressed in terms of ordinary fermion operators as $c_{i,\sigma}(1 - n_{i,-\sigma})$. To clarify the nature of the low-energy spin excitations, we applied the following scheme: using the Lanczos algorithm we computed the dynamical spin correlation function (SCF)

$$S(\mathbf{q}, \omega) = \sum_{\nu} |\langle \Psi_{\nu,n} | S^z(\mathbf{q}) | \Psi_{0,n} \rangle|^2 \delta(\omega - (E_{\nu,n} - E_{0,n})), \quad (1)$$

where $|\Psi_{\nu,n}\rangle (E_{\nu,n})$ is the ν^{th} eigenstate (eigenenergy) with n holes (in particular $\nu=0$ implies the ground state). Fig. 1 shows $S(\mathbf{q}, \omega)$ in the 18-site cluster with 2 and the 16-site cluster with 4 holes (in this paper we restrict ourselves to these systems, whose behaviour is representative). We then extract the energies $E_{\nu,n}$ of the dominant low-energy peaks indicated by arrows in Fig. 1, these are the two lowermost peaks for each cluster. Each of them is a single, unsplit peak so that a unique (and for the low energy peaks highly precise) value for $E_{\nu,n}$ can be obtained. Using the inverse iteration algorithm [5] we can now converge out the corresponding final state wave function $|\Psi_{\nu,n}\rangle$ (using a reasonably accurate estimate E_{tr} for an eigenvalue, the inverse iteration method essentially consists in applying powers of $(H - E_{tr})^{-1}$ to some trial state). Thereby we also obtain an independent estimate for $E_{\nu,n}$, which always agreed with the value extracted from the correlation function to an accuracy better than 10^{-10} , essentially the limit of the Lanczos procedure; total spin and point group symmetry of the obtained $|\Phi_{\nu}\rangle$ were cross-checked to be compatible with the selection rules. In the last step we calculated (again via the Lanczos method) the electronic spectral functions $A^{(\alpha)}(\mathbf{k}, \omega) = A_{n,-}^{(\alpha)}(\mathbf{k}, -\omega) + A_{n,+}^{(\alpha)}(\mathbf{k}, \omega)$, where

$$\begin{aligned} A_{n,-}^{(\alpha)}(\mathbf{k}, \omega) &= \sum_{\mu} |\langle \Psi_{\mu,n+1} | \hat{c}_{\mathbf{k},\sigma} | \Psi_{\alpha} \rangle|^2 \delta(\omega - (E_{\mu,n+1} - E_{0,n})), \\ A_{n,+}^{(\alpha)}(\mathbf{k}, \omega) &= \sum_{\mu} |\langle \Psi_{\mu,n-1} | \hat{c}_{\mathbf{k},\sigma}^\dagger | \Psi_{\alpha} \rangle|^2 \delta(\omega - (E_{\mu,n-1} - E_{0,n})). \end{aligned} \quad (2)$$

where $|\Psi_{\alpha=0}\rangle$ denotes the n -hole ground state and $|\Psi_{\alpha=1}\rangle$ the SCF-final state. These functions are simply the

photoemission (PES) and inverse photoemission (IPES) spectra for the ground state and SCF-final state. By inspection of the difference $A_d(\mathbf{k}, \omega) = A^{(1)}(\mathbf{k}, \omega) - A^{(0)}(\mathbf{k}, \omega)$ (which henceforth will be referred to as the ‘difference spectrum for the state $|\Psi_{\nu,n}\rangle$ ’) we can now decide whether the creation of a spin excitation is associated with the transfer of single particle spectral weight in the band near the Fermi energy or not.

To begin with, Fig. 2 shows the single particle spectral function of the ground state and the difference spectrum for the SCF final state for momentum transfer $\mathbf{q} = (2\pi/3, 2\pi/3)$. In order to eliminate shifts of spectral weight on small energy scales, a relatively large Lorentzian broadening of $0.4t$ is used. We locate the Fermi energy as separating the highest PES and lowest IPES peaks in the ground state spectra. The difference spectra have remarkably small weight as compared to the original spectra, particularly the parts remote from E_F : small ‘wiggles’, indicate slight shifts of ‘peaks’ within the PES spectrum. Major changes of the spectral function are restricted to the neighborhood of E_F : at $\mathbf{k}_1 = (-2\pi/3, 0)$, PES weight is shifted to the IPES side right at E_F , indicating that at this momentum the SCF-final state has a reduced electron occupancy of the quasiparticle band as compared to the ground state. At $\mathbf{k}_1 + \mathbf{q} = (0, 2\pi/3)$ the reverse can be seen, i.e. the SCF-final state has an enhanced electron occupancy of the quasiparticle band. We thus see a shift of low energy spectral weight with momentum transfer $\mathbf{q}$, precisely the expected signature of a particle-hole excitation. To a lesser degree, such a shift can also be seen between $(\pi/3, -\pi/3)$ and $(\pi, \pi/3)$, but the weight transfer is substantially smaller.

The particle-hole character is even more pronounced for the low energy spin excitation with momentum transfer $\mathbf{q} = (\pi/2, \pi/2)$ in the 16-site cluster with 4 holes (Fig. 3) where we clearly see the transfer of an electron right at E_F from $(\pi, 0)$ to $(\pi/2, -\pi/2)$. We conclude that our technique indeed provides a sensitive tool for detecting particle hole excitations and consequently apply it to the dominant low energy peak at (π, π) . The difference spectra for the respective final states in the 18 and 16-site clusters are shown in Figs. 4 and 5. There are ‘wiggles’ near the Fermi energies in some of them which indicate a shift of the quasiparticle peaks. There is, however, no appreciable shift of weight from PES to IPES near the Fermi energy, despite the fact that the spectral intensity of these excitations in $S(\mathbf{q}, \omega)$ is much stronger than the particle-hole excitations considered previously. The spin excitation at (π, π) thus obviously is not associated with a shift of spectral weight near the Fermi energy, i.e. it is not a particle-hole excitation but rather a collective mode the character of which remains to be clarified.

Up to a constant, the spin correlation function for this momentum equals the correlation function of the staggered magnetization, $M_S = \sum_{i \in A} S_i^z - \sum_{i \in B} S_i^z$. We will now assume that the ground state expectation value $\langle M_S^2 \rangle = (N \cdot m_S)^2$, where N denotes the number of sites

and m_S is of order unity, and show that this allows the explicit construction of a low energy collective spin excitation with momentum transfer (π, π) (we do not assume $\langle M_S \rangle \neq 0$, i.e. there need not be broken symmetry). We decompose the ground state wave function $|\Psi_0\rangle$ as $|\Psi_0\rangle = \sum_{\nu} g_{\nu} |\psi_{\nu}\rangle$, where the $|\psi_{\nu}\rangle$ are defined by the requirements $M_S |\psi_{\nu}\rangle = \nu |\psi_{\nu}\rangle$ and $\langle \psi_{\nu} | \psi_{\nu} \rangle = 1$. In other words, we decompose the ground state into components with fixed value of the staggered magnetization. We define the matrix elements of the Hamiltonian, $h_{\nu,\mu} = \langle \psi_{\nu} | H | \psi_{\mu} \rangle$, and obviously have $h_{\nu,\mu} = 0$ for $|\nu - \mu| > 2$ (the Hamiltonian can change the staggered magnetization at most by 2). The requirement that the ground state energy E_0 be extensive then implies $h_{\mu,\nu} \sim N$.

Introducing the translation operator by one lattice site, $T_{1,0}$, the translational invariance of $|\Psi_0\rangle$ guarantees that $g_{\nu} T_{1,0} |\psi_{\nu}\rangle = g_{-\nu} |\psi_{-\nu}\rangle$. We now define the trial state $|\Psi_1\rangle = \sum_{\nu>0} (g_{\nu} |\psi_{\nu}\rangle - g_{-\nu} |\psi_{-\nu}\rangle)$. By construction this state changes sign under $T_{1,0}$, i.e. it has momentum (π, π) . The expectation values of the Hamiltonian with $|\Psi_0\rangle$ and $|\Psi_1\rangle$ differ by $\Delta H = h_{0,0} g_0^2 + 4h_{1,0} g_1 g_0 + 4h_{2,0} g_2 g_0 + \dots + 4h_{1,-1} g_1 g_{-1}$, the norms of these state differ by $\Delta N = g_0^2$. The energy $\Delta = (\Delta H + E_0 \Delta N) / (1 - \Delta N)$ thus provides a rigorous upper bound for the energy difference between ground state and lowest state with total momentum (π, π) and restricting the Hilbert space to $|\Psi_0\rangle$ and $|\Psi_1\rangle$ we find $S(\mathbf{Q}, \omega) \sim m_S^2 \delta(\omega - \Delta)$.

Fig. 6 shows different forms of the probability distribution g_{ν}^2 which are compatible with the requirement that $\langle M_S^2 \rangle = \sum_{\nu} \nu^2 g_{\nu}^2 \sim N^2$. Form (a) implies that $g_{\nu} = 0$ for $\nu \sim 0$ so that $\Delta=0$. Hence $|\Psi_0\rangle$ and $|\Psi_1\rangle$ are degenerate and e.g. the state $|\Psi_+\rangle = \sum_{\nu>0} g_{\nu} |\psi_{\nu}\rangle$ by itself is already an eigenstate: this corresponds to true broken symmetry. Form (b) implies a nonvanishing Δ ; here the number of g_{ν}^2 which differ from 0 must be of order N , so that $g_{\nu} \sim 1/\sqrt{N}$ and hence $\Delta \sim N^0$: we have a potentially low energetic collective mode in the spin excitation spectrum for all system sizes, which corresponds to a change of the relative phase of the two components of the ground state wave function with positive and negative staggered magnetization. If g_{ν}^2 continuously approaches the broken symmetry form (a), the excitation energy of this mode will approach zero. For completeness we note that $\langle M_S^2 \rangle \sim N$ (as is the case for a free electron gas) would imply $\Delta \sim \sqrt{N}$, so that we cannot get a meaningful low energy mode from the above construction.

Let us now check this interpretation of the (π, π) mode. The exact diagonalization technique gives $|\Psi_0\rangle$ directly as a linear combination of basis states $\hat{c}_{i_1, \sigma_1}^{\dagger} \hat{c}_{i_2, \sigma_2}^{\dagger} \dots \hat{c}_{i_n, \sigma_n}^{\dagger} |vac\rangle$, so that it is easy to construct the state $|\Psi_1\rangle$ (normalized to unity). We can then compute its overlap with the SCF final state for momentum transfer (π, π) , $|\Psi_{SCF}\rangle$, i.e. the quantity $|\langle \Psi_1 | \Psi_{SCF} \rangle|^2$. Results for various cluster sizes and dopings are summarized in Tab. I, which quite obviously confirms our hypothesis: there is always a substantial overlap between

the respective $|\Psi_1\rangle$ and the exact SCF final state, and for hole concentrations around 10% (2 holes) this overlap is quite comparable to that in the undoped Heisenberg antiferromagnet, where we can expect that the (π, π) mode will evolve into the spin wave mode for infinite system size. The finite energy collective mode, which we could predict on quite general assumptions thus indeed seems to be realized in the small clusters. From our general construction we expect that this mode persists also in the infinite system and thus may explain the neutron scattering experiments.

In summary, our results show a fairly complicated picture of the spin excitation spectrum in the doped two-dimensional $t-J$ model. For low doping levels, (i.e. 2 or 4 holes) the dominant low energy mode is located at (π, π) , and we have identified this mode as a collective mode comparable to the spin waves present in the undoped cluster. Away from (π, π) on the other hand, we have fairly conventional particle-hole excitations.

The fact that parts of the spin excitation spectrum of the Heisenberg antiferromagnet persist in the doped system appears very natural if one adopts the picture that the doped system should be modelled as an incoherent ‘spin background’ in which spin-bag-like quasiparticles corresponding to the doped holes are moving [6]. Then, it seems natural to distinguish between two types of spin excitations: the first are the particle-hole excitations of the hole-liquid, which should resemble that of a Fermi liquid with a Fermi surface volume proportional to the number of holes. This part of the excitation spectrum can quantitatively explain the Pauli susceptibility at low temperatures [7]. In addition there are the excitations of the ‘spin background’ which may, with some modifications, resemble that of the Heisenberg antiferromagnet. One example here is the spin wave-like mode at (π, π) , a possible other example the ‘two magnon’ excitation observed in the Raman spectrum until well in the superconducting doping regime [8].

To conclude, we note that the general scheme developed above allows for a highly selective study of the character of arbitrary low energy excitations; it thus seems possible (at least in principle) to obtain a fairly complete picture of the entire low-energy excitation spectrum of the 2-d $t - J$ model clusters.

It is a pleasure for us to acknowledge numerous instructive discussions with Professor S. Maekawa. Financial support of R. E. by the Japan Society for the Promotion of Science is most gratefully acknowledged. Parts of the calculations were carried out at the Computer Center of the Institute for Molecular Science, Okazaki.

- [3] T. Tohyama and S. Maekawa, Phys. Rev. B **49**, 3596 (1994).
- [4] M. Yu. Kuchiev and O. P. Sushkov, SISSA-preprint cond-mat 9406105.
- [5] see e.g. A. Jennings, Matrix Computations for Engineers and Scientists, John Wiley & Sons, Chichester New York Brisbane Toronto (1977)
- [6] R. Eder and Y. Ohta, to appear in Phys. Rev. B.
- [7] S. Trugman, Phys. Rev. Lett. **65**, 500 (1990).
- [8] G. Blumberg *et al.*, Phys. Rev. B **49**, 13295 (1994).

FIG. 1. Spin correlation function in the 18-site cluster with 2 holes (top) and the 16 site cluster with 4 holes (bottom).

FIG. 2. Difference spectrum for the SCF final state in the 18-site cluster with 2 holes with momentum $(\frac{2\pi}{3}, \frac{2\pi}{3})$. The black (gray) area corresponds to IPES (PES). Also shown is the single particle spectral function for the ground state (full line: PES, dotted line: IPES). The vertical line marks the Fermi energy.

FIG. 3. Difference spectrum for the SCF final state in the 16-site cluster with 4 holes with momentum $(\frac{\pi}{2}, \frac{\pi}{2})$. All conventions are like in Fig. 2.

FIG. 4. Difference spectrum for the SCF final state in the 18-site cluster with 2 holes with momentum (π, π) . All conventions are like in Fig. 2.

FIG. 5. Difference spectrum for the SCF final state in the 16-site cluster with 4 holes with momentum (π, π) . All conventions are like in Fig. 2.


FIG. 6. Two possible forms of the ‘wave function’ g_ν . (a) implies broken symmetry, (b) implies no broken symmetry.


TABLE I. Overlap of the exact SCF-final state and the trial state based on the spin-wave picture for different cluster sizes and dopings. 20 sites and 4 holes exceeds our computer capacity.


	16-site	18-site	20-site
0 holes	0.8378	0.7560	0.8214
2 holes	0.7187	0.7388	0.7059
4 holes	0.4346	0.5620	


[1] J. Rossat-Mignod *et al.*, Physica B **169**, 58 (1991).

[2] E. Dagotto *et al.*, Phys. Rev. B **45**, 10741 (1992).












Fig. 6

